

Kansarhaye Afra (Privately Held Co)

Mining and Industrial Complex

Typical Analysis	
Free Moisture (105 °C, 2hours), Wt %	4.0-7.0
pH (5% Suspension)	6.5-9.0
Apparent Bulk Density, Kg/m ³	0.55-0.80
Specific Gravity	1.5-1.7

Physical Specification	
Particle Size	200 Mesh
Appearance	White Powder
Application	This kind of Activated clay is used for animal feed, especially effective in absorbing Aflatoxins, fungal toxins, Zearalenone and Ochratoxin and used for Pellet binder due high swelling
Packaging (Kg)	In 25 kg Bag and 850 Kg Bulk Bag(for export)

Price Product (Grade: 10311N)
27 kg packaging
300 dollars per ton for ADS bag without the pallet, and an additional 20 dollars is added for each pallet

Analysis Report

Grade: 10311N

(Feed grade)

Chemical Composition (Expressed as percentage of oxides by Weight)	
SiO ₂ , %	61.54
AL ₂ O ₃ , %	13.3
Fe ₂ O ₃ , %	4.92
MgO, %	3.68
CaO, %	1.95
Na ₂ O, %	0.71
K ₂ O, %	0.06
Loss On Ignition (LOI), %	13.98

